

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
31 January 2002 (31.01.2002)

PCT

(10) International Publication Number
WO 02/08158 A1

(51) International Patent Classification⁷: C07C 2/00, 5/00,
C10G 35/02, 35/04, 35/06, 35/085, 35/09, C10L 1/00

(74) Agents: HUGHES, Gerard, J. et al.; Exxon Research
and Engineering Company, P.O. Box 390, Annandale, NJ
08801 (US).

(21) International Application Number: PCT/US01/22739

(22) International Filing Date: 19 July 2001 (19.07.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/220,093 21 July 2000 (21.07.2000) US
09/897,192 2 July 2001 (02.07.2001) US

(71) Applicant: EXXONMOBIL RESEARCH AND ENGI-
NEERING COMPANY [US/US]; 1545 Route 22 East,
P.O. Box 900, Annandale, NJ 08801 (US).

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BZ, CA, CH, CR, CU, CZ, DE, DK, EE,
ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP,
KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD,
MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD,
SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN,
YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF,
CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(72) Inventors: BAIRD, William, Chalmers, Jr.; 13343 High-
land Road, Baton Rouge, LA 70810 (US). CHEN, Jing-
guang, G.; 321 Detjen Drive, Hockessin, DE 19707 (US).
MCVICKER, Gary, Brice; 65 Main Street, P.O. Box 427,
Califon, NJ 07830 (US).

(54) Title: NAPHTHENE RING OPENING OVER GROUP VIII METAL CATALYSTS CONTAINING CRACKING MODERA-
TORS

(57) Abstract: Disclosed is a process for opening naphthenic rings of naphthenic ring-containing compounds, along with catalysts which can be used in that process. The naphthene ring opening catalyst is a catalyst which comprises at least one of a Group VII metal selected from Ir, Pt, Pd, Rh, and Ru in an amount effective to ring open naphthene rings on naphthene ring-containing compounds, the metal being supported on a substrate comprising at least one Group IB, IIB, and IVA metal in an amount effective to moderate cracking of a naphthene ring-containing feed to form methane.

WO 02/08158 A1

**NAPHTHENE RING OPENING OVER GROUP VIII
METAL CATALYSTS CONTAINING CRACKING MODERATORS**

5 FIELD OF THE INVENTION

[0001] This invention relates to a method and composition for opening naphthenic rings of naphthenic ring-containing compounds such as distillate. In particular, this invention relates to the use of a catalyst composition comprising at least one Group VIII metal supported on a material containing at least one of a Group IB, IIB, and Group IVA metal.

BACKGROUND OF THE INVENTION

15 [0002] There is an increasing demand for hydrocarbons boiling in the distillate boiling point range ("distillate"). Distillates typically contain paraffins, naphthenes, and aromatics. For fuel quality parameters such as cetane number, gravity and emissions, paraffins are the most desirable components, followed by naphthenes, followed by aromatics. The least desirable are multi-ring aromatic compounds.

20 There is also an increasing demand for paraffinic solvents arising from their low toxicity and biodegradability. Consequently, it is desirable to reduce the cyclic compound content of hydrocarbon solvent blends, in general, and to convert naphthenes to paraffins, in particular. The general process of converting naphthenes to paraffins is referred to herein as ring opening.

25 [0003] Refinery processes that produce distillate fuels have a limited capability to produce high quality and yields of distillate fuel. For example, conventional hydrogenation processes saturate aromatic rings to form naphthenes, thereby increasing the cetane number and increasing the API gravity (i.e., lowering the density). However, single ring and multi-ring naphthenes have generally lower

30 cetane values and are denser than paraffins having substantially the same number of

- 2 -

carbon atoms. The greater density of naphthenes results in reduced volume of the distillate fuel blend relative to compositions containing similar concentrations of paraffins instead of naphthenes. Hydrocracking catalysts, typically composed of hydrogenation metals supported on acidic supports, are also effective for aromatics
5 hydrogenation and for ring opening by cracking. However, cracking tends to make lower boiling point products, including a significant quantity of undesired gas by-products, which lowers the overall boiling range and limits the volume of final distillate product. In fact, hydrocracking products generally do not contain more distillate boiling range paraffins than the hydrocracking feeds. Moreover, a
10 significant portion of the total paraffin concentration in the final product of conventional hydrocracking processes, including gas by-products, are relatively low molecular weight compounds that are outside the distillate boiling range. Thus, the apparent increase in distillate boiling range paraffins and improved distillate fuel quality may result primarily from a combination of the hydrogenation of aromatics
15 and a concentration of paraffins in a reduced volume of distillate product, the latter arising from removing the undesired paraffin gas by-product, i.e., the low boiling point paraffin gas components.

[0004] There is, therefore, a need for selective ring opening processes for
20 converting single and multi-ring aromatic species, including alkyl functionalized derivatives thereof, into distillate boiling range paraffins without producing a significant amount of undesirable low boiling point saturated species. Selectivity for ring opening is related to the propensity for cleavage of a ring bond which results in product molecules having an equivalent number of carbon atoms and at least one less
25 ring than the original molecule, rather than cleavage of a bond which results in a product molecule having fewer carbons than the original molecule. A perfectly selective ring opening process would give only ring bond cleavage to produce molecules having an equivalent number of carbon atoms and at least one less ring

- 3 -

than the original molecule. For example, from a hydrocarbon stream containing only single ring naphthenes of n number of carbon atoms, the product from perfect ring opening selectivity would contain only paraffins of n number of carbon atoms.

Thus, the greater number of product molecules from a ring opening process having an equivalent number of carbon atoms and at least one less ring than the original molecule, the greater the selectivity for ring opening.

[0005] Conventional ring opening processes use a wide range of catalysts, including bifunctional metal hydrogenation-acidic catalysts. Distillate quality may be improved by controlling paring isomerizations and subsequent dealkylations in order to limit the number of lower cetane, highly branched paraffins that may result from conventional ring opening.

[0006] Some conventional processes for forming an improved distillate employ Ir catalysts for opening naphthene ring compounds. Even though distillates such as diesel, jet fuel and heating oil contain at least about 20 vol.%, generally about 20 to about 40 vol.% of C₆ naphthenes, the conventional processes open C₆ naphthenes at low rates, if at all. This problem is exacerbated with hydrotreated distillates because they have a still greater concentration of C₆ naphthenes. In order to overcome this problem of poor opening of C₆ naphthene rings, U.S. Patent No. 5,763,731 teaches using Ir along with at least one acidic co-catalyst, preferably a zeolite, to isomerize the C₆ naphthene rings to C₅ rings. However, since the resulting C₅ ring structure will typically bear increased numbers of substituents, such as alkyl groups, this approach increases the volume of branched paraffins upon ring opening. In addition, the presence of an acidic co-catalyst has a tendency to isomerize any naturally present linear paraffin into a branched paraffin, often resulting in a ring-opened product that has an undesirably high concentration of branched paraffins. Moreover,

- 4 -

the process results in increased light saturated gas production, particularly at high temperature.

[0007] Another conventional process, set forth in U.S. Patent No. 5,811,624, uses
5 Ir along with at least certain transition metals for isomerizing C₆ naphthene rings to
C₅ naphthene rings, with the Ir component being particularly effective for opening
the C₅ naphthene rings. However, the product contains a significant concentration of
branched paraffins, which leads to a lower product cetane number. There is still a
need, therefore, for a ring opening process and catalyst which provide a much higher
10 degree of linear paraffin functionality in the ring opened product, and at the same
time, provide a greater volume of product in the distillate range.

SUMMARY OF THE INVENTION

15 [0008] In one embodiment, a ring opening catalyst and process are provided to
form a reduced number of ring structures in the product stream, minimize
dealkylation of any pendant substituents optionally present on the ring structure, and
increase volume of the product. In particular, the invention is beneficial in that it
provides a relatively high content of more linear paraffins in the product. In one
20 embodiment, the invention provides paraffins having a more linear (i.e., less
branchy) character than conventional methods and catalysts using feeds containing
both C₅ and C₆ naphthene ring compositions having tertiary carbons. The ring-
opened product provides a diesel or jet fuel product, which has a high degree of
linear and less branched paraffins, particularly one having a high degree of linear and
25 less branched C₉⁺ paraffins. This translates to a fuel product which is high in cetane
number, a highly sought after fuel quality.

- 5 -

[0009] Specifically, a highly selective catalyst, which is provided for converting naphthene feed into paraffin product containing a substantial quantity of linear and less branched paraffins, with a relatively low methane yield. The invention is particularly beneficial in converting a naphthene feed containing a C₆ naphthene ring-containing composition, wherein the C₆ ring contains at least one tertiary carbon, to a product containing a substantial quantity of linear and less branched paraffin compounds.

[0010] In one embodiment there is provided a catalyst which comprises a Group VIII metal selected from Ir, Pt, Pd, Rh, Ru, and combinations thereof, in an amount effective to ring open a naphthene ring of a naphthene ring-containing compound, the metal being supported on a substrate comprising at least one of a Group IB, IIB, and IVA metal in an amount effective to moderate cracking of a naphthene ring-containing feed to form methane. Desirably, the Group VIII metal is present in a range of about 0.01 to about 10.0 wt.%. In a preferred embodiment, the Group VIII metal is present in a range of about 0.1 to about 7.0 wt.%, more preferably in a range of about 0.3 to about 6.0 wt.%, and most preferably in a range of about 0.3 to about 5.0 wt.%.

[0011] In another preferred embodiment, the substrate contains a refractory inorganic oxide. Preferably, the refractory inorganic oxide is at least one of alumina, silica, zirconia, titania, chromia, zinc oxide, magnesia, thoria, boria, silica-alumina, silica-magnesia, chromia-alumina, alumina-boria, silica-zirconia. More preferably, the substrate is alumina.

[0012] The Group IB metal is preferably at least one of Cu, Ag, and Au. The Group IIB metal is preferably Zn. The Group IVA metal is preferably selected from

- 6 -

Ge, Sn, Pb. Therefore, the metal is preferably selected from Cu, Ag, Au, Zn, Ge, Sn, Pb, and combinations thereof.

5 [0013] Desirably, the total amount of cracking moderator (i.e., the total amount of any Group IB, IIB, and IVA metal present) in the catalyst ranges from about 0.01 to about 5.0 wt.%. Preferably, the cracking moderator is present in a range of about 0.01 to about 3.0 wt.%, more preferably in a range of about 0.01 to about 2.0 wt.%, and most preferably in a range of about 0.01 to about 1.0 wt.%.

10 [0014] In a more preferred embodiment, the Group VIII metal is Ir and the cracking moderator is Cu or Sn. In an alternative embodiment, the Group VIII metal is Pt and the cracking moderator is Cu or Sn. In yet another embodiment, the Group VIII metal is a combination of Pt and Ir and the cracking moderator is Sn.

15 [0015] A process is also provided for opening naphthene rings of naphthene ring-containing compounds in a feed stream. The process comprises providing a naphthene ring-containing feed stream, and contacting the naphthene ring-containing feed stream with a catalyst of the invention. In a desirable embodiment, the method further comprises ring opening naphthene rings having at least one tertiary carbon
20 site at the tertiary carbon site, thereby forming a ring opened product having increased linear paraffin functionality relative to that of the feed stream.

[0016] The method may also include recovering the ring opened product. The ring opened product may be used directly, for example, as a diesel fuel, jet fuel, gas
25 oil, and heating oil, and it may also be blended with other petroleum streams for use, for example, as a diesel fuel, jet fuel, gas oil, and heating oil. Preferably, the ring opened product is blended with a petroleum stream having a boiling point of about 175°C to about 600°C, wherein the blend has a cetane number of at least about 40.

- 7 -

[0017] Ring opening may be carried out at a temperature ranging from about 150°C to about 400°C; a total pressure ranging from about 100 to about 3,000 psig; a space velocity ranging from about 0.1 to about 10 V/V/Hr; and a hydrogen treat gas rate ranging from about 200 to about 10,000 standard cubic feet per barrel (SCF/B). The feed stream in the ring opening process is preferably a petroleum feed stream which has a boiling point of from about 175°C to about 600°C, more preferably about 175 to about 500°C.

10 [0018] Preferably, the ring opening catalysts of the invention are capable of ring opening at least about 20% of an amount of 1,2-dimethylcyclohexane at the tertiary carbon site. More preferably, the ring opening catalysts are capable of ring opening between about 30% and about 40% of the amount of 1,2-dimethylcyclohexane at the tertiary carbon site.

15

[0019] The invention further relates to a product made by the ring opening process. The product is higher in linear paraffin functionality compared to conventional ring opened products.

20

DETAILED DESCRIPTION OF THE INVENTION

[0020] The invention is based in part on the discovery of ring opening catalyst compositions useful in processes for forming high cetane number distillate having a desirable concentration of compounds, which have a high degree of linear paraffin functionality. Increasing ring opening process severity, for example, by increasing reaction temperature, is known to increase the yield of ring opened product. However, as severity increases, the yield from undesirable side reactions also increases, leading to an undesirable increase in the yield of light saturated products

- 8 -

such as methane. This invention relates in part to the suppression of such side reactions by using ring opening catalysts containing at least one Group VIII metal and at least one of a Group IB, IIB, and IVA metal. In a preferred embodiment, the catalyst compositions are useful for opening rings at tertiary carbon sites in naphthene or naphthenic ring-containing distillates in order to form products with a high degree of linear paraffin functionality. The compositions are especially effective in opening compounds containing C₅ and C₆ naphthene rings bearing at least one tertiary carbon.

10 [0021] As defined herein, compounds having a high degree of linear paraffin functionality have fewer paraffin (i.e., alkyl) side chains and longer paraffin substituents. According to this definition, linear paraffins, particularly C₁₀-C₂₀ linear paraffins, are the most highly desirable compounds for use as a diesel or jet fuel product, though other compounds having a relatively high degree of linear paraffin
15 functionality are also acceptable. For example, a cycloalkane ring compound having a single, linear alkyl side chain has relatively high paraffin functionality compared to a cycloalkane ring having multiple side chains. By the same definition, an aromatic ring compound having a single, linear alkyl side chain has a relatively high linear paraffin functionality compared to an aromatic ring compound having multiple side
20 chains.

[0022] As defined herein, a tertiary carbon (3° carbon) is the site of location of a substituent group on a naphthenic ring compound. Tertiary carbons are represented by such structural features, for example, as

25 —CH(R)—CH₂— and —CH(R)—CH(R)— where R is a carbon-containing chain, preferably a C₁-C₁₀ carbon-containing chain.

- 9 -

[0023] Opening the ring structure of naphthenic ring compounds at the tertiary carbon site, known as tertiary bond cleavage, is particularly desirable for C₆ naphthenic rings. Tertiary bond cleavage is advantageous because isomerization of the C₆ rings to C₅ rings is abated so that the ring-opened product will have a high
5 degree of linear paraffin functionality.

[0024] As used herein, a naphthene or a naphthenic ring-containing composition refers to a cycloalkane or a composition containing at least one cycloalkane ring in its structure. For example, the term can refer to either a C₅ or C₆ ring-membered
10 cycloparaffin. The cycloparaffin can also include various side chains, particularly one or more alkyl side chains of 1-10 carbons. In addition the cycloparaffin can be attached or fused to other ring structures, forming two or three membered ring compounds. The additional ring members can be saturated or unsaturated, as long as at least one ring of the complete structure contains a tertiary carbon. Examples of
15 two and three membered ring structures that can contain a tertiary carbon include saturated or partially saturated naphthalenes, indenenes, fluorenes, phenanthrenes, anthracenes, acenaphthalenes, and biphenylenes.

[0025] A feedstream which is to be ring opened will typically contain a mix of
20 hydrocarbons having one or more of the naphthene ring-containing compositions, and the naphthene ring-containing compositions preferably contain at least one alkyl substituent. Preferably, the feedstream will comprise at least 5 vol.% of at least one naphthenic ring-containing compound more preferably at least 25 wt.%, most preferably at least 50 wt.%. Typically the feedstream will comprise from about 5 to
25 about 85 vol.% of at least one naphthenic ring-containing compound, based on the volume of the feedstream.

- 10 -

[0026] In a more preferred embodiment, the hydrocarbon containing the naphthene ring compositions that are to be opened will include C₅ and C₆ naphthene ring compounds that do not include additional ring members. Non-limiting examples of these compounds include methylcyclopentanes, ethylcyclopentanes, propylcyclopentanes, butylcyclopentanes, pentylcyclopentanes, methylcyclohexanes, ethylcyclohexanes, propylcyclohexanes, butylcyclohexanes, and pentylcyclohexanes. Preferably, the C₅ and C₆ ring naphthene ring compounds contain alkyl substituents.

[0027] Naphthenic ring-containing compounds are found in a wide variety of hydrocarbon feeds, such as petroleum streams boiling in the distillate range. These streams will typically include a variety of chemical compounds, including multi-ring compositions. Preferably, this invention uses a petroleum feed stream having a boiling point ranging from about 175°C to about 600°C. Examples of such a feed stream include diesel fuel, jet fuel, heating oil, gas oil, and light cycle oil. Gas oil includes vacuum gas oil boiling in the range from about 340°C to about 565°C, which is typically derived from vacuum distillation of crude oil, or it can be obtained by conversion of products such as coker gas oil or heavy cat cycle oil. Other feed streams can also be used if appropriately pre-treated. These streams include chemical feed streams and lube streams.

[0028] In particular, the process provides Group VIII-based ring opening catalysts which exhibit desirable tertiary bond cleavage, and which moderate or suppress undesirable methane formation. This moderation of methane formation leads to the formation of higher cetane number paraffinic species in the reaction product. The Group VIII-based ring opening catalysts incorporate an effective amount of hydrogenolysis suppressors (i.e., cracking suppressors) such as the Group IB, IIB, and IVA metals in order to form the higher cetane paraffin product. An effective amount in this context is the amount of Group IB, IIB, and IVA metal to suppress

- 11 -

undesirable hydrogenolysis side reactions. As undesirable hydrogenolysis products may be readily identified by conventional methods, the effective amount of Group IB, IIB, and IVA metal may be readily determined.

5 [0029] Polymetallic catalysts such as Group VIII-Group IB, Group VIII-Group IIB, and Group VIII-Group IVA catalysts are preferred as effective ring opening catalysts. The catalysts exhibit improved cracking patterns at severe process conditions, and in particularly preferred embodiments, the formation of less branched paraffins.

10

[0030] In one embodiment, the naphthene ring opening catalysts of this invention comprise at least one of the Group VIII metals, preferably at least one of Ir, Pt, Pd, Ru, and Rh, supported on a material (i.e., a substrate) containing the Group IB metals, such as Cu, Ag, Au, the Group IIB metals, such as Zn, or the Group IVA
15 metals, such as Sn, all of which can be used alone or in mixtures thereof. Preferred Group VIII metals are Ir, Pt, and Ru, more preferred Group VIII metals are Ir and Pt. Particularly preferred cracking moderators are Cu, Sn, or Zn, all of which can be used alone or in mixtures thereof.

[0031] The Group VIII metal (or metals) is present in the catalyst in an amount
20 effective to ring open naphthene rings on naphthene ring-containing compounds. The total loading of the Group VIII metal catalyst components can range from about 0.01 to about 10 wt.%. Total loadings of about 0.1 to about 7.0 wt.% are preferred; loadings of about 0.3 to about 6.0 wt.% are more preferred; and loadings of about 0.3 to about 5.0 wt.% are most preferred.

25

[0032] In a preferred embodiment, the catalyst preferably comprises Ir in combination with at least one other or "second" Group VIII metal selected from Pt, Ru, and Rh. In a preferred embodiment, the other Group VIII metal is Pt. The Ir and

- 12 -

the other Group VIII metal are present in an amount effective for opening a naphthene ring at a tertiary carbon site. Desirably, Ir is present in a range of about 0.1 to about 2.0 wt.%, preferably in a range of about 0.3 to about 1.5 wt.%, more preferably in a range of about 0.5 to about 1.2 wt.%, and most preferably in a range of about 0.5 to about 1.0 wt.%, based on the weight of the ring opening catalyst. It is also desirable that the second Group VIII metal be present in a range of about 0.001 to about 2.0 wt.%, preferably in a range of about 0.005 to about 1.5 wt.%, more preferably in a range of about 0.007 to about 1.3 wt.%, and most preferably in a range of about 0.01 to about 1.0 wt.%, based on the weight of the ring opening catalyst.

[0033] The cracking moderator is present in an amount effective to moderate cracking of a naphthene ring-containing feed to form methane. Desirably, the cracking moderator is also present in an amount effective for enhancing ring opening of the naphthene ring-containing compounds which contain a tertiary carbon site. The total loading of the Group IB, IIB or IVA metals (i.e., the total cracking moderator loading) can range from about 0.01 to about 5.0 wt.%, based on the total weight of the catalyst. Total loadings of about 0.01 to about 3.0 wt.% are preferred; loadings of about 0.01 to about 2.0 wt.% are more preferred; and loadings of about 0.01 to about 1.0 wt.% are most preferred. Preferred, but not limiting, catalyst compositions within these limits include Ir-Cu, Ir-Sn, Pt-Ir-Sn, Pt-Cu, and Pt-Sn.

[0034] The naphthene ring opening catalysts can be supported on conventional refractory supports. Particularly desirable supports are refractory inorganic oxides. Non-limiting examples of refractory inorganic oxides include alumina, silica, zirconia, titania, chromia, zinc oxide, magnesia, thoria, boria, silica-alumina, silica-magnesia, chromia-alumina, alumina-boria, silica-zirconia, and combinations thereof. Low-acidity support materials such as alumina are preferred.

- 13 -

[0035] In a particularly preferred embodiment, the alumina support is prepared by digesting high purity alumina hydrate powder in a weak organic acid, thereby forming an alumina sol which is then spray-dried by a conventional spray-drying technique to produce the alumina hydrate powder. If the alumina hydrate powder is not of appropriate particle size, it can be ground by any conventional grinding means for reducing the particle size of refractory powders. The alumina hydrate powder is then blended with an effective amount of water, or sol, to form a paste of sufficient consistency for extrusion. The alumina paste is then extruded into an appropriate shape, such as pellets, dried and calcined at temperatures from about 400°C to about 650°C. The metals can be introduced in any one or more of the above process steps. A more complete description of this process is described in U.S. Pat. No. 5,015,614, which is incorporated herein by reference.

[0036] In one embodiment of the invention, the Group VIII metal and the cracking moderator may be supported on a modified substrate. The modified substrate may be prepared by incorporating therein an effective amount of modifier. The modifier is such that, when used in an effective amount, it contributes to the resulting ring opening catalyst an improved overall selectivity with respect to linear and less branched paraffin yield, with simultaneous suppression of isomerization reactions when compared to an identical catalyst not containing such modifiers. In other words, the term "effective amount of modifier" as used herein refers to the concentration range of modifier which, when used in a ring opening process, will improve the selectivity to linear and less branched paraffin formation from naphthene rings and reduce isomerization of linear paraffins. Preferred elements that can be incorporated as modifiers into the substrate for the purposes of this invention include Cs, Mg, Ca, and Ba. Ca, Mg, and Ba are more preferred, with Mg being most preferred.

- 14 -

[0037] Generally, the modifier concentration in the ring opening catalyst will be at least about 0.1 to about 50 wt.%. Preferably, the modifier concentration in the ring opening catalyst will be about 0.5 to about 40 wt.%, more preferably about 1 to about 30 wt.%, and most preferably about 2 to about 25 wt.%. The modifier component can be incorporated into the substrate during any stage of production.

[0038] The modifier is preferably added to the substrate material as aqueous solutions of their common salts, preferably nitrates, nitrites, oxides, hydroxides, halides, carboxylates, and the like using either incipient wetness or absorption from solution techniques. Incipient wetness is a preferred procedure. Although the modifier can be added to the substrate material after extrusion of the substrate, it is preferable to add modifier prior to extrusion to ensure homogeneity of the modifier elements throughout the substrate.

[0039] The modified substrate compositions of this invention are also characterized as having: (i) a surface area greater than about 50 m²/g, preferably from about 100 to about 700 m²/g, and more preferably from about 100 to about 300 m²/g; (ii) a bulk density from about 0.3 to about 1 g/ml, preferably from about 0.4 to about 0.8 g/ml; (iii) an average pore volume from about 0.2 to about 1.1 ml/g, preferably from about 0.3 to about 0.8 ml/g; and (iv) an average pore diameter from about 30 to about 300 Angstroms.

[0040] The addition of the Group VIII metal(s) and the cracking moderator (i.e., the Group IB, IIB, and IVA metals) to the support material may be accomplished by conventional techniques. Preferred techniques include incipient wetness impregnation and absorption from excess aqueous solution. Alternatively, the metals may be incorporated into the support material during its preparation as disclosed and

- 15 -

claimed in U.S. Pat. No. 4,963,249, the description of which is incorporated herein by reference.

[0041] The Group IB, IIB, and IVA metals may be added in metal precursor
5 form, such as in the form of metal halides, nitrates, nitrites, oxides, hydroxides, carboxylates, and the like. This method of preparation is described in detail in U.S. Pat. No. 4,231,898, the description of which is incorporated herein by reference.

[0042] The Group VIII metal(s) may also be added in precursor form. Suitable
10 metal precursors are the halides, the halometallic acids, nitrates, nitrites, amine halo complexes, amine nitrate complexes, and amine nitrite complexes.

[0043] Incipient wetness is a particularly desirable method for incorporating the
desired level of Group VIII metal into the modified substrate. The metal is
15 preferably dissolved in solution, desirably in precursor form. Metal deposition from organic solvents may also be practiced using organometallic complexes such as acetylacetonates, carbonyls and the like. Once the metal complexes have been impregnated, they are decomposed by thermal treatment in an air, hydrogen, or inert atmosphere. This can be accomplished by conventional heating or by the application
20 of microwave or ultrasonic radiation. The decomposition of the metal complex will leave the Group VIII metal impregnated in the substrate.

[0044] The naphthene ring opening catalysts may be activated according to conventional methods. For example, they may be activated by drying in air at a
25 temperature ranging from about ambient temperature to about 300°C for about 4 to about 24 hours and reducing in-flowing hydrogen, preferably in situ, at a temperature ranging from about 200°C to about 600°C for about 0.5 to about 24 hours. Drying at

- 16 -

temperatures below 200°C and reducing at about 350°C to about 500°C for about 4 hours are preferred.

[0045] As discussed, the preferred ring opening catalyst compositions are useful in processes for forming high cetane number distillate having a desirable concentration of compounds which have a high degree of linear paraffin functionality. To convert naphthene compounds to paraffins, a catalytically effective amount of at least one catalyst of this invention is contacted with an appropriate feed stream under catalytic ring opening conditions. Preferred conditions are such that the C₅ and C₆ rings of the naphthene compounds are opened when contacted with the catalyst. While conventional process conditions may be employed, preferred process conditions include a temperature ranging from about 150°C to about 400°C, preferably from about 225°C to about 350°C, a total pressure ranging from about 100 to about 3,000 psig, preferably from about 100 to about 2,200 psig; more preferably about 100 to about 1,500 psig, a liquid hourly space velocity ranging from about 0.1 to about 10 V/V/Hr, preferably from about 0.5 to about 5 V/V/Hr, and a hydrogen treat gas rate ranging from about 200 to about 10,000 SCF/B, preferably about 500 to about 5000 SCF/B. SCF/B means standard cubic feet per barrel, and V/V/Hr means volume of feed per volume of catalyst per hour.

20

[0046] Conventional ring opening reactors may be used in the ring opening process of this invention. A fixed bed reactor system wherein the feedstock is passed over one or more stationary beds of catalyst is preferred. Multiple reactors may be used in either series or parallel configurations.

25

[0047] Hydrogen gas (i.e., a hydrogen-containing treat gas) conducted to the reaction process may flow over the catalyst either in a direction co-current or countercurrent with the feedstock. Hydrogen is supplied to saturate the carbons

- 17 -

where ring opening occurs, and it is preferably supplied in stoichiometric excess. In one embodiment, the reactor effluent is passed to a separation zone where hydrogen that has not been consumed in the reaction process is separated and suitably recycled to the reaction zone together with make-up hydrogen as needed. In another
5 embodiment, the treat gas is employed in a "once-through" arrangement and is therefore not recycled.

[0048] Countercurrent reactors incorporating the catalyst are a preferred embodiment, since properly constructed countercurrent reactors can provide better
10 contacting of reactants and treat gas. They are particularly beneficial in maintaining a low H_2S partial pressure. Such a reactor is disclosed in U.S. Patent No. 5,942,197, the description of which is incorporated herein by reference. This preferred design is less susceptible to flooding than conventional countercurrent reactors because it incorporates passageways to bypass one or more catalyst beds. Bypass of at least a
15 portion of the hydrogen treat gas is designed to occur when the pressure differential across the catalyst bed increases to a predefined threshold correlating to a near-flood condition. When gas bypasses the catalyst bed, the pressure differential across the catalyst bed decreases to permit the downward flow of liquid. When the pressure differential falls below a predefined level, the bypassing of gas is automatically
20 stopped.

[0049] It is preferred that the feed streams be hydrotreated prior to ring opening to reduce sulfur content to low levels, preferably less than about 10 ppm, more preferably less than about 1 ppm, most preferably less than about 0.1 ppm. This is
25 particularly desirable when high sulfur feeds are used in the ring opening process, since the ring opening catalysts are sensitive to high sulfur content.

- 18 -

[0050] Hydrotreating to reduce sulfur is referred to herein as hydrodesulfurization. Conventional hydrodesulfurization catalysts may be used to reduce the sulfur content of feed containing sulfur compounds to the preferred levels.

5 [0051] Non-limiting examples of conventional hydrodesulfurization catalysts which may be used to reduce the sulfur content of the feed include catalysts which comprise a Group VI metal with one or more Group VIII metals as promoters, the metals being on a refractory support. Conventional hydrodesulfurization processes are conducted at pressures ranging from about 50 to about 2000 psig, preferably
10 from about 100 to about 1500 psig, liquid hourly space velocities ranging from about 0.2 to about 6 V/V/Hr, and a hydrogen gas rate of about 200 to about 5000 SCF/B (standard cubic feet per barrel). The liquid hourly space velocity is based on the volume of feed per volume of catalyst per hour, i.e., V/V/Hr.

15 [0052] Sulfur sorbents, including regenerable sulfur sorbents, may also be used to reduce the sulfur content of the feed. These materials are capable of removing the easy sulfur compounds, particularly hydrogen sulfide, under relatively mild sulfur removing conditions. Examples of sulfur sorbents include metal oxides. These systems are disclosed in U.S. Pat. No. 5,928,498; 5,925,239; 5,935,420; 4,003,823;
20 U.S. Pat. No. 4,007,109; U.S. Pat. No. 4,087,348; U.S. Pat. No. 4,087,349; U.S. Pat. No. 4,119,528; and U.S. Pat. No. 4,127,470 all of which are incorporated by reference herein.

[0053] If significant aromatic compounds are present in the feed stream, it is
25 desirable to saturate them. It is preferred that the feedstock contain less than about 20 wt.% total aromatic compounds, preferably less than about 15 wt.%, more preferably less than about 10 wt.%.

- 19 -

[0054] The aromatics saturation (ASAT) process may be performed in one or a series of reactors either before or after the ring opening process, since either mode will generally result in a product having increased cetane number due to the lowering of the aromatic content. Saturation of aromatics in the feed is preferred, however, 5 prior to the ring opening process. This is because saturation of aromatics tends to result in the formation of additional naphthenes, providing additional material that can ultimately be converted using the catalyst of this invention to form compounds having a higher degree of linear paraffin functionality. In another preferred embodiment, a hydrodesulfurization reactor will be placed in front of the aromatics 10 saturation reactor so that the catalyst in the aromatics saturation reactor will contact low sulfur feedstock.

[0055] Any conventional aromatic saturation process may be used to hydrogenate the aromatic rings of the aromatic compounds in connection with one embodiment. 15 Typical conditions for saturating aromatics-containing feedstocks include temperatures from about 150°C to about 400°C, pressures from about 100 to about 2000 psig, space velocities from about 0.4 to 6 V/V/Hr, and hydrogen gas rates from about 200 to about 6000 standard cubic feet per barrel (SCF/B). Lower temperatures are found to be most desirable for the hydrogenation or saturation reactions since 20 nonselective cracking reactions thereby are minimized. Selective saturation of the aromatics results in a saturated intermediate from the hydrogenation zone usually containing less than 15 weight % total aromatics.

[0056] Ring opening may also be practiced in a variety of stacked or mixed bed 25 configurations along with aromatics saturation and sulfur removal. The stacked and mixed beds can occupy a single reactor or multiple reactors, and may take place in either co-current or countercurrent mode. The stacking of fixed beds of catalyst refers to the sequence of beds disposed with respect to the direction of flow of the

- 20 -

liquid phase reactants. In a single reactor, such beds would be vertically disposed from top to bottom. In a series of reaction vessels the sequence is defined by the flow of the liquid phase.

- 5 [0057] A reactor may, for example, be loaded to have stacked layers of a sulfur reducing catalyst (e.g., a hydrodesulfurization (HDS) catalyst); a sulfur sorbent (sorbent); an aromatics saturation (ASAT) catalyst; and/or a ring opening (RO) catalyst. Specific examples of stacked catalyst arrangements include: HDS/ASAT/sorbent/RO; HDS/RO/ASAT; sorbent/ASAT/RO; and
- 10 HDS/sorbent/ASAT/RO. Preferred mixed bed catalyst arrangements include: RO + ASAT; sorbent + RO; sorbent + ASAT + RO; and sorbent + HDS + RO. Conditions favoring the ring opening function are preferred.

- [0058] The ring opened product may be recovered after the final processing step,
- 15 i.e., after ring opening, after an optional ASAT final step, or after any further optional treatment step, according to conventional methods. The recovered product may be used directly, for example, as a diesel fuel, jet fuel, gas oil, and heating oil, and it can be blended with other petroleum products and used, for example, as a diesel fuel, jet fuel, gas oil, and heating oil. When blended, it is preferred that the
- 20 ring opened product be blended with a petroleum stream having a boiling point of about 175°C to about 600°C, wherein the blend has a cetane number of at least about 40.

- [0059] The Periodic Table of the Elements referred to herein appears on the
- 25 inside cover page of the Merck Index, 12th Ed., Merck & Co., 1996.

- 21 -

[0060] This invention will be better understood with reference to the following examples, which are intended to illustrate specific embodiments within the overall scope of the invention as claimed.

5 GENERAL EXPERIMENTAL

[0061] In the examples, tertiary bond cleavage (%) is determined by dividing the wt.% yield of ring opened products involving tertiary centers by the total wt.% yield of all ring opened products and multiplying by 100. For example,
10 methylcyclohexane ("MCH") tertiary bond cleavage in the examples = $100 \times (\text{wt.\% n-heptane} / (\text{wt.\% n-heptane} + \text{wt.\% isoheptanes}))$; for 1,2-dimethylcyclohexane ("1,2 DMCH") tertiary bond cleavage = $100 \times ((\text{wt.\% n-octane} + \text{wt.\% 3-methylheptane}) / (\text{wt.\% n-octane} + \text{wt.\% 3-methylheptane} + \text{wt.\% 2,3-dimethylhexane} + \text{wt.\% 3,4-dimethylhexane}))$. Metal loadings are in weight percent,
15 based on the weight of the catalyst. For example, a catalyst of 0.9 wt.% Ir and 0.9 wt.% Pt, based on the weight of the catalyst is written as 0.9 Ir-0.9Pt.

Example 1 (comparative)

20 [0062] A 0.9 wt.% Ir/Al₂O₃ ring opening catalyst was prepared by impregnating 50 g of reforming grade alumina with 28 ml of a chloroiridic stock solution containing 16 mg Ir/ml. The catalyst was dried at 120°C for 24 hr and reduced at 450°C for 3 hr. The catalyst was used to ring open methylcyclohexane under the following conditions: 300°C, 200 psig, 10 W/H/W, H₂/Oil = 6. The results are found
25 in the Table 1.

Example 2

[0063] A 0.9Ir-0.03Cu/Al₂O₃ catalyst was prepared as in Example 1 with copper nitrate being added to the Ir solution. The catalyst was dried at 120°C for 24 hr and reduced at 450°C for 3 hr. The catalyst was used to ring open methylcyclohexane, and the results are found in the Table 1.

Example 3

10 [0064] A 0.9Ir-0.1Cu/Al₂O₃ catalyst was prepared as in Example 1 with copper nitrate being added to the Ir solution. The catalyst was dried at 120°C for 24 hr and reduced at 450°C for 3 hr. The catalyst was used to ring open methylcyclohexane, and the results are found in the Table 1.

15 **Example 4**

[0065] A 0.9Ir-1.0Cu/Al₂O₃ catalyst was prepared as in Example 1 with copper nitrate being added to the Ir solution. The catalyst was dried at 120°C for 24 hr and reduced at 450°C for 3 hr. The catalyst was used to ring open methylcyclohexane, and the results are found in Table 1.

20

Table 1

Example	Catalyst	Conversion, Wt. %	C ₇ Paraffin Yield, Wt. %	C ₁ Yield, Wt. %	C ₇ Paraffin Yield/C ₁ Yield
1	0.9Ir	58	30	4	8
2	0.9Ir-0.03Cu	33	21	2	11
3	0.9Ir-0.1Cu	20	13	1	15
4	0.9Ir-1.0Cu	3	0	1	---

- 23 -

[0066] Examples 1-4 illustrate that the addition of Cu decreases the activity of the Ir catalyst. However, the influence of Cu on cracking to methane is substantial and decreases the formation of this undesirable product by about 50-75%. Furthermore, the selectivity to ring opened paraffins over Ir-Cu exceeds that of the exclusively Ir-containing catalysts by about 20-25%, and the ratio of the paraffin to methane selectivity represents a 50-90% increase for the Ir-Cu catalysts. The results further demonstrate that a critical balance is required between the Ir and Cu content of the catalyst as the 1.0 wt.% Cu catalyst is significantly deactivated.

10 Example 5

[0067] A 0.9Ir-0.3Sn catalyst was prepared as in Example 1 by impregnating 50g of alumina containing 0.3 wt.% Sn. The Sn-alumina was synthesized as described in U.S. Patent No. 4,963,249. The catalyst was dried at 120°C for 24 hr and reduced at 15 450°C for 3 hr. The catalyst was then used to ring open methylcyclohexane under the following conditions: 300°C, 200 psig, 10 W/H/W, H₂/Oil = 6. The results are detailed in Table 2.

Table 2

Example	Catalyst	Conversion, Wt. %	C ₇ Paraffin Yield, Wt. %	C ₁ Yield, Wt. %	C ₇ Paraffin Yield/C ₁ Yield
1	0.9Ir	58	30	4	8
5	0.9Ir-0.3Sn	47	39	1	44

[0068] These data illustrate that given a comparable amount of conversion, the Ir-Sn catalyst has a higher yield of ring opened paraffins, while the methane yield is decreased by 75%. Thus, the Ir-Sn catalyst acquires an extremely favorable paraffin to methane selectivity benefit.

Example 6

[0069] A 0.6Pt-0.6Ir catalyst was prepared as in Example 1, and used to ring open
5 methylcyclohexane under the following conditions: 300°C, 800 psig, 10 W/H/W,
H₂/Oil = 6. The results are summarized in the Table 3.

Example 7

10 [0070] A 0.6Pt-0.6Ir-0.1Sn catalyst was prepared as in Example 1, and then used
to ring open methylcyclohexane. The results are summarized in the Table 3.

Table 3

Example	Catalyst	Conversion, Wt. %	C ₇ Paraffin Yield, Wt. %	C ₁ Yield, Wt. %	C ₇ Paraffin Yield/C ₁ Yield
1	0.9Ir	61	53	0.9	58
6	0.6Pt-0.6Ir	59	50	0.6	85
7	0.6Pt-0.6Ir-0.1Sn	49	43	0.4	111

15

[0071] Comparison of the catalysts of Examples 1 and 6 at approximately
equivalent conversions show the Pt-Ir catalyst of Example 6 to be a more selective
catalyst than the exclusively Ir-containing catalyst. The addition of Sn, Example 7,
decreases activity modestly, but affords a significant increase in selectivity due to the
20 suppression of cracking to methane, a benefit that is evident in the paraffin to
methane selectivity value.

- 25 -

Example 8

[0072] A 2.0Pt-0.3Sn catalyst was prepared with a process similar to Example 5, by impregnating 50g of a 0.3 wt.% Sn containing alumina with 36 ml of a chloroplatinic acid stock solution, 28 mg, Pt/ml. The catalyst was dried at 120°C for 24 hr and reduced at 450°C for 3 hr. The catalyst was used to ring open methylcyclohexane under the following conditions: 350°C, 800 psig, 1 W/H/W, H₂/Oil = 6. The results are shown in Table 4.

10 **Example 9**

[0073] A 5.0Pt-0.3Sn catalyst was prepared with a process similar to Example 5, by impregnating 50 g of a 0.3 wt.% Sn containing alumina with 89 ml of a chloroplatinic acid stock solution, 28 mg Pt/ml. The catalyst was dried at 120°C for 24 hr and reduced at 450°C for 3 hr. The catalyst was used to ring open methylcyclohexane under the following conditions: 350°C, 800 psig, 1 W/H/W, H₂/Oil = 6. The results are found in the Table 4.

Table 4

Example	Catalyst	Conversion, Wt. %	C ₇ Paraffin Yield, Wt. %	C ₁ Yield, Wt. %	C ₇ Paraffin Yield/C ₁ Yield
1	0.9Ir	61	53	0.9	58
8	2.0Pt-0.3Sn	56	13	0.06	240
9	5.0Pt-0.3Sn	61	14	0.02	769

[0074] The results demonstrate that at approximately equivalent conversion the Pt-Sn catalysts have low ring opening activity relative to the exclusively Ir-containing catalysts. However, the Pt-Sn catalysts also have exceptionally low

- 26 -

cracking activity, which can be noted in an extremely favorable paraffin to methane selectivity. The bulk of the conversion over the Pt-Sn catalysts is ring isomerization.

Example 10

5

[0075] The catalyst of Example 8 was used to ring open methylcyclohexane at high reaction temperatures than prior examples in order to increase the ring opening activity of the catalyst. The results are presented in Table 5.

10 **Example 11**

[0076] The catalyst of Example 9 was used to ring open methylcyclohexane at high reaction temperatures to increase the ring opening activity of the catalyst. The results are presented in Table 5.

15

Table 5

Example	Catalyst	R/O Temp, °C	Conversion, Wt. %	C ₇ Paraffin Yield, Wt. %	C ₁ Yield, Wt. %	C ₇ Paraffin Yield/C ₁ Yield
1	0.9Ir	300	61	53	0.9	58
8	2.0Pt-0.3Sn	350	56	13	0.06	240
9	5.0Pt-0.3Sn	350	61	14	0.02	769
10	2.0Pt-0.3Sn	400	86	73	0.5	142
11	5.0Pt-0.3Sn	400	78	65	0.2	280

[0077] Examples 10 and 11 illustrate that at high severity process conditions the catalysts of this invention achieve high ring opening activity while maintaining

20

- 27 -

cracking to methane yields of less than that of the Ir-containing catalyst which operates at temperatures 100°C cooler. The use and operation of the Ir-containing catalyst at the temperatures shown for the Pt-Sn catalysts leads to extensive cracking and methane yields in excess of 50 wt.%. The Pt-Sn catalysts are clearly capable of operation at high temperature conditions while retaining a high paraffin to methane ratio selectivity benefit.

[0078] Table 6 presents comparative data for the catalysts of the preceding Table 5 which show that catalysts of Examples 8-11 ring open methylcyclohexane to a lesser branched product than does the exclusively Ir-containing catalyst. This is reflected in the degree of tertiary bond cleavage leading to the formation of n-heptane as contrasted with the cleavage of non-tertiary bonds leading to the formation of isoheptanes.

- 28 -

CLAIMS:

1. A naphthene ring opening catalyst comprising a Group VIII metal selected from Ir, Pt, Pd, Rh, Ru, and combinations thereof, in an amount effective to
5 ring open a naphthene ring of a naphthene ring-containing compound, the metal being supported on a substrate comprising at least one of a Group IB, IIB, and IVA metal in an amount effective to moderate cracking of a naphthene ring-containing feed to form methane.
- 10 2. The naphthene ring opening catalyst of claim 1, wherein the Group VIII metal is present in a range from about 0.01 to about 10.0 wt.%.
3. The naphthene ring opening catalyst of claim 1, wherein the substrate contains at least one refractory inorganic oxide selected from alumina, silica,
15 zirconia, titania, chromia, zinc oxide, magnesia, thoria, boria, silica-alumina, silica-magnesia, chromia-alumina, alumina-boria, silica-zirconia.
4. The naphthene ring opening catalyst of claim 3, wherein the substrate contains alumina.
20 5. The naphthene ring opening catalyst of claim 3, wherein the substrate contains at least one of Cs, Mg, Ca, and Ba in an amount ranging from about 0.1 to about 50 wt.%, based on the weight of the catalyst.
- 25 6. The naphthene ring opening catalyst of claim 1, wherein the Group IB, IIB, and IVA metal is at least one of Cu, Ag, Au, Zn, Ge, Sn, and Pb in an amount ranging from about 0.01 to about 5.0 wt.%, based on the weight of the catalyst.

- 29 -

7. The naphthene ring opening catalyst of claim 1, wherein the Group VIII metal is a combination of Pt and Ir and the Group IB, IIB, and IVA metal is Sn.

8. The naphthene ring opening catalyst of claim 1, wherein the Group
5 VIII metal is Ir and the Group IB, IIB, and IVA metal is Sn.

9. A process for opening naphthene rings of naphthene ring-containing compounds in a feed stream, comprising:

providing a naphthene ring-containing feed stream; and

10 contacting the naphthene ring-containing feed stream with a catalyst which comprises a Group VIII metal selected from Ir, Pt, Pd, Rh, Ru, and combinations thereof, in an amount effective to ring open a naphthene ring of a naphthene ring-containing compound, the metal being supported on a substrate comprising at least one of a Group IB, IIB, and IVA metal in an amount effective to moderate cracking
15 of a naphthene ring-containing feed to form methane.

10. The process of claim 9, wherein the Group VIII metal is present in a range from about 0.01 to about 10.0 wt.%.

20 11. The process of claim 9, wherein the substrate contains at least one refractory inorganic oxide selected from alumina, silica, zirconia, titania, chromia, zinc oxide, magnesia, thoria, boria, silica-alumina, silica-magnesia, chromia-alumina, alumina-boria, silica-zirconia.

25 12. The process of claim 11, wherein the substrate contains alumina.

13. The process of claim 11, wherein the substrate contains at least one of Cs, Mg, Ca, and Ba in an amount ranging from about 0.1 to about 50 wt.%, based on

- 30 -

the weight of the catalyst.

14. The process of claim 9, wherein the Group IB, IIB, and IVA metal is selected from Cu, Ag, Au, Zn, Ge, Sn, Pb and combinations thereof in an amount
5 ranging from about 0.01 to about 5.0 wt.%, based on the weight of the catalyst.

15. The process of claim 9, wherein the Group VIII metal is a combination of Pt and Ir and the Group IB, IIB, and IVA metal is Sn.

10 16. The process of claim 9, wherein the Group VIII metal is Ir and the Group IB, IIB, and IVA metal is Sn.

17. The process of claim 9, wherein ring opening is carried out at a temperature of from about 150°C to about 400°C, a total pressure from about 100 to
15 about 3,000 psig, a liquid hourly space velocity from about 0.1 to about 10 V/V/Hr, a hydrogen treat gas rate from about 200 to about 10,000 standard cubic feet per barrel (SCF/B), and wherein the feed stream is a petroleum feed stream which has a boiling point ranging from about 175°C to about 600°C.

20 18. The process of claim 7, further comprising recovering the ring opened product.

19. The process of claim 18, further comprising blending the ring opened product with a petroleum stream having a boiling point ranging from about 175°C to
25 about 600°C, wherein the blend has a cetane number of at least about 40.

20. The process of claim 9, wherein the petroleum feed stream is at least one of diesel fuel, jet fuel, heating oil, vacuum gas oil, and light cycle oil.

- 31 -

21. The process of claim 9, wherein the naphthene ring-containing feed stream has a sulfur content of less than about 10 ppm and contains less than about 20 wt.% total aromatic compounds,

5 22. A product made by the process of claim 18.

23. A product made by the process of claim 19.

INTERNATIONAL SEARCH REPORT

Int. application No.
PCT/US01/02739

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : Please See Extra Sheet.

US CL : 585/700, 940; 208/133, 134, 137, 138, 15

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 585/700, 940; 208/133, 134, 137, 138, 15

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WEST

search terms: naphthene\$, "ring opening", Ir, Pt, Pd

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,928,498 A (MCVICKER ET AL) 27 July 1999 (27/07/99), See column 3, lines 65-67, column 4, lines 1-11 and 55-62, column 5, lines 1-15 and 45-47 and column 6, lines 1-15.	1-23
X	US 5,763,731 A (MCVICKER ET AL) 09 June 1998 (09/06/98), See column 1, lines 10-35, column 6, lines 30-40, column 7, lines 29-40, column 9, lines 46-56 and column 11, lines 14-25.	1-4, 6, 9-12, 14 and 17-23
A	US 5,345,026 A (CHANG ET AL) 06 September 1994 (06/09/94), See entire document.	1-23
A	US 5,811,624 A (HANTZER ET AL) 22 September 1998 (22/09/98), See entire document.	1-23

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"G" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

26 SEPTEMBER 2001

Date of mailing of the international search report

01 NOV 2001

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3930

Authorized officer

NADINE PREISCH

Telephone No. (703) 308-0661

INTERNATIONAL SEARCH REPORT

Int. application No.
PCT/US01/02739

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5,925,239 A (KLEIN ET AL) 20 July 1999 (20/07/99), See entire document	1-23
A	US 5,935,420 A (BAIRD, JR ET AL) 10 August 1999 (10/08/99), See entire document	1-23

INTERNATIONAL SEARCH REPORT

In ional application No.
PCT/US01/22739

A. CLASSIFICATION OF SUBJECT MATTER:
IPC (7):

C07C 2/00, 5/00; C10G 35/02, 35/04, 35/06, 35/085, 35/09; C10L 1/00